


Bekaert Steel Fibres: **Wiremix® W50** product data sheet

DESCRIPTION

Bekaert steel fibres are filaments of wire, deformed and cut to lengths for reinforcement of concrete



GEOMETRY

Product	W50
Loose (L) Glued (G)	L
Hooked (H) Undulated (U)	U
Length ¹⁾ L _{nom} (mm)	50 (±3% tolerance)
Width (mm)	2,00 - 2,90
Min. wire tensile strength (N/mm ²)	500


Values are indicative only. Modifications reserved. All details describe our products in general form only.

PACKAGING



PALLET: 1000 kg (40x25kg)

STORAGE



DOSING AND MIXING

- A continuous grading is preferred
- A preliminary test is advised
- Mix until all fibres are distributed uniformly

TRANSPORT OF ALL PRODUCTS

Truck transport: max. load

- 20 pallets / truck
- 22 big-bags / truck

Sea transport: containers

- 20 big-bags / 40 ft container
- 20 pallets / 40 ft container

CUSTOMER SERVICE

NV Bekaert SA www.bekaert.com/building
infobuilding@bekaert.com
 Bekaertstraat 2
 BE-8550 Zwevegem T+32 56 76 61 10
 Belgium F+32 56 76 79 47

All Bekaert company names are trademarks owned by NV Bekaert SA Zwevegem - Belgium. Modifications reserved. All details describe our products in general form only. For ordering and design only use official specifications and documents.

© 2008 Bekaert
 Design by Boa-inc.be
 72.16.05